



### Technical specifications

| POLYURETHANE FINISH          | Results               | Norms       |
|------------------------------|-----------------------|-------------|
| Nominal thickness            | 1.0 mm                | EN 438-2.4  |
| Grade (145°C)                | Postformable          | EN 438-2.21 |
| Bending radius               |                       |             |
| - longitudinal               | 20 mm                 |             |
| - transversal                | 20 mm                 |             |
| Weight                       | 1.2 Kg/sqm            |             |
| Dimensional variations:      |                       | EN 438-2.9  |
| - longitudinal               | 0.4 %                 |             |
| - transversal                | 1.1 %                 |             |
| Abrasion resistance          | > 150 Taber rev.      | EN 438-2.6  |
| Boiling water resistance     | moderate effect       | EN 438-2.7  |
| Stain resistance:            |                       | EN 438-2.15 |
| - acetone, trichloroethylene | evident effect        |             |
| - group 2,3,4 – procedure A  | no effect             |             |
| Lightfastness (Xenotest)     | > 3 grey scale        | UNI 9427    |
| Formaldehyde emission        | according to the rule | EN 717-2    |