



### Technical specifications

WAX EFFECT FINISH	Results	Norms
Nominal thickness	1.0 mm	EN 438-2.4
Grade (145°C)	Postformable	EN 438-2.21
Bending radius		
- longitudinal	20 mm	
- transversal	20 mm	
Weight	1.2 Kg/sqm	
Dimensional variations:		EN 438-2.9
- longitudinal	0.4 %	
- transversal	1.2 %	
Abrasion resistance	> 80 Taber rev.	EN 438-2.6
Stain resistance:		EN 438-2.15
- acetone, trichloroethylene	no effect	
- group 2,3,4 – procedure A	no effect	
Lightfastness (Xenotest)	> 3 grey scale	UNI 9427
Formaldehyde emission	according to the rule	EN 717-2